

COMPARISON OF FASTNESS PROPERTIES AND COLOUR STRENGTH OF DYED COTTON FABRICS WITH ECO-FRIENDLY NATURAL DYES

ABSTRACT

Bleached cotton fabric was dyed with natural dyes obtained from the flower of *Spathodeacampanulata* and *Cordia sebestena*. The colour fastness properties and colour strength of dyed cotton fabric were determined and compared. From the comparative study of fastness properties and colour strength of the dyed cotton samples, *Spathodea campanulata* in simultaneous mordanting method with 3% mordant combination gives better results as compared to the natural dye obtained from the flower of *Cordia sebestena*.

Keywords: *Cordia sebestena*, Cotton, Fastness, Mordants, Natural dye, *Spathodea campanulata*

INTRODUCTION

Until about 150 years ago all dyes were natural substances, derived mainly from plants and animals. The natural dyes present in plants and animals are pigmentary molecules (Sandeep Bains et al, 2003) which impart colour to the materials. Recently, interest in the use of natural dyes has been growing rapidly due to the result of stringent environmental standards imposed by many countries in response to toxic and allergic reactions associated with synthetic dyes (Anitha et al, 2007).

There are several plants/plant parts that provide natural dyes which are used in the textile industry. However, the common drawbacks of natural dyes are their non-reproducible and non-uniform shades, poor to moderate colour fastness and lack of scientific information on the chemistry of dyeing and standardised dyeing methods (Gulrajani et al, 1992). Many reports are available on application of natural dyes on cotton (Anderson, 1971; Adeel et al, 2009; Kumaresan et al 2011).

The present investigation deals with the extraction of natural dyes from the flower of *Spathodea campanulata* and flower of *Cordia sebestena* grow in all warm and damp parts of India.

The aim of present work has been carried out to prepare eco-friendly natural dyes from the flower of *Spathodea campanulata* and flower of *Cordia sebestena* and apply them on cotton fabric (Kumaresan et al 2011). In the present work an attempt has been made to study the effect of mordanting and dyeing properties (Mahangade et al, 2009) of cotton fabrics such as, washing, rubbing, light fastness and perspiration (Goodarzian, et al, 2010) and also to visualize the effect of myrobolan and metallic mordants have been undertaken.

MATERIALS AND METHODS

Materials:

Bleached cotton fabric obtained from Khadhi Trust, Dindugal, was used for this study. Analytical reagents (AR) grade ferrous sulphate, aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, commercial grade acetic acid, common salt, sodium carbonate were used. A natural mordant myrobolan (*Terminalia chebula*) powder was used for the study. Depending upon the mordant used, the colour obtained on textiles from the flower of *Spathodea campanulata* and flower of *Cordia sebestena* extracts may give different shades.

Methods: Extraction of colour component:

For optimizing (Vankar et al, 2009) the extraction method the ethanol extraction of dye liquor was carried out under varying conditions, such as time of extraction, temperature of extraction bath and material-to-liquor ratio. In each case, the optical density or absorbance value at a particular maximum absorbance wavelength ($\lambda_{420\text{nm}}$) for the ethanol extract of plant parts were estimated by using Hitachi-U-2000 UV-VIS absorbance spectrometer.

Dyeing of cotton fabrics with the extract of flower of *Spathodea campanulata* and flower of *Cordia sebestena*:

The wetted out cotton samples were entered into dye baths containing required amount of dye extract and water. After 10 minutes, required amount of sodium carbonate and sodium chloride were added. The dyeing was carried out for one hour at 60°C. The dyed samples were dried in air without washing to make them ready for pre, simultaneous and post-mordanting using myrobolan and metallic salts.

Pre-Mordanting of cotton fabric with myrobolan and metallic salts:

Bleached cotton fabric with or without pre-mordanting were further mordanted prior to dyeing using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20. The samples treated with metal salts were dyed with the dye extract.

Simultaneous mordanting of cotton fabric with myrobolan and metallic salts:

Bleached cotton fabrics were treated with both dye extract and metal salts simultaneously, using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20.

Post-Mordanting of cotton fabrics with myrobolan and metallic salts:

Bleached cotton fabrics were dyed with dye extract. The wetted out cotton samples were entered into different dye baths containing required amount of dye extract and water. After 10 minutes required amount of sodium sulphate was added. After 20 minutes required amount of sodium chloride was added. The dyeing was carried out for one hour at 50°C. The dyed samples were taken out, squeezed and used for treatment with metal salts process without washing. The dyed cotton samples were treated with different metal salts using 1-3% of any one of the chemical mordants, such as aluminium sulphate, nickel sulphate, potassium dichromate, stannous chloride, copper sulphate and the myrobolan, at 60°C for 30 min with material-to-liquor ratio of 1:20.

In all the above three methods, after the dyeing is over, the dyed samples were repeatedly washed with water and then dried in air. Finally, the dyed samples were subjected to soaping with 2gpl soap solution at 50°C for 10 min, followed by repeated water wash and drying under sun.

Determination of surface colour strength (K/S value):

The K/S value of the undyed and dyed cotton fabrics was determined (Kumaresan et al, 2011) by measuring surface reflectance of the samples using a computer-aided Macbeth 2020 plus reflectance spectrophotometer, using the following Kubelka Munk equation with the help of relevant software:

$$K/S = \frac{(1 - R_{\lambda, \max})^2}{2R_{\lambda, \max}} = \alpha C$$

where K is the coefficient of absorption; S the coefficient of scattering; C_d , the concentration of the hue and $R_{\lambda, \max}$ the surface reflectance value of the sample at a particular wavelength, where maximum absorption occurs for a particular dye/colour component.

Evaluation of Colour Fastness:

Colour fastness to washing of the dyed fabric samples was determined as per IS: 764 – 1984 method using a Sasmira launder-O-meter following Is-3 wash fastness method. The wash fastness rating was assessed using grey scale as per ISO-05-A02 (loss of shade depth) and ISO-105-A03 (extent of staining) and the same was cross-checked by measuring the loss of depth of colour and staining using Macbeth 2020 plus computer-aided colour measurement system attached with relevant software. Colour fastness to rubbing (dry and wet) was assessed as per IS: 766-1984 method using a manually operated crock meter and grey scale as per ISO-105-A03 (extent of staining).

Colour fastness to exposure to light was determined as per IS: 2454-1984 method. The sample was exposed to UV light in a Shirley MBTF Microsal fade-O-meter (having 500 watt Philips mercury bulb tungsten filament lamp simulating day light) along with the eight blue wool standards (BS 1006: BOI: 1978). The fading of each sample was observed against the fading of blue wool standards (1-8).

RESULTS AND DISCUSSION

The colour strength values of cotton fabrics dyed with the natural dyes obtained from the flower of *Spathodea campanulata* and flower of *Cordia sebestena* by using single mordanting method are presented and compared in Tables 1, 2 and 3.

Mordant concentration:1%	K/S($\lambda=420$ nm)					
	Pre mordanting		Simultaneous mordanting		Post mordanting	
	SC	CS	SC	CS	SC	CS
Nickel sulphate	1.45	1.62	2.39	2.44	2.12	2.32
Aluminium sulphate	1.76	1.80	2.58	2.63	2.56	2.51
Potassium dichromate	1.21	1.15	1.28	1.21	1.36	1.18
Ferrous sulphate	1.79	1.87	2.89	2.92	2.75	2.78
Stannous chloride	1.66	1.70	2.58	2.62	2.41	2.51
Myrobolan	1.04	1.10	1.25	1.32	1.31	1.29

Table 1: Surface colour strength of *Spathodea campanulata* (SC) and *Cordia sebestena* (CS) dyed cotton fabric after pre, simultaneous and post mordanting methods by using 1% mordant concentration. K/S value without mordant: Cotton-1.53(SC), 1.47(CS).

Mordant concentration:2%	K/S($\lambda=420$ nm)					
	Pre mordanting		Simultaneous mordanting		Post mordanting	
	SC	CS	SC	CS	SC	CS
Nickel sulphate	1.51	1.53	2.42	2.45	2.18	2.21
Aluminium sulphate	1.81	1.84	2.65	2.69	2.59	2.62
Potassium dichromate	1.28	1.32	1.33	1.34	1.39	1.41
Ferrous sulphate	1.89	1.91	2.75	2.79	2.68	2.71
Stannous chloride	1.71	1.73	2.63	2.66	2.48	2.51
Myrobolan	1.05	1.13	1.32	1.35	1.37	1.31

Table 2 : Surface colour strength of *Spathodea campanulata* (SC) and *Cordia sebestena* (CS) dyed cotton fabric after pre, simultaneous and post mordanting methods by using 2% mordant concentration. K/S value without mordant: Cotton-1.53(SC), 1.47(CS)

Mordant concentration:3%	K/S($\lambda=420$ nm)					
	Pre mordanting		Simultaneous mordanting		Post mordanting	
	SC	CS	SC	CS	SC	CS
Nickel sulphate	1.56	1.60	2.47	2.52	2.22	2.26
Aluminium sulphate	1.85	1.91	2.71	2.75	2.65	2.69
Potassium dichromate	1.33	1.35	1.42	1.46	1.39	1.41
Ferrous sulphate	1.96	2.01	2.89	2.91	2.86	2.78
Stannous chloride	1.76	1.79	2.68	2.71	2.54	2.58
Myrobolan	1.14	1.17	1.36	1.39	1.41	1.47

Table 3: Surface colour strength of *Spathodea campanulata* (SC) and *Cordia sebestena* (CS) dyed cotton fabric after pre, simultaneous and post mordanting methods by using 3% mordant concentration. K/S value without mordant: Cotton-1.53(SC), 1.47(CS).

From the results, it was observed that among the two plant parts, *Cordia sebestena* showed better colour strength values. In all the three dyeing methods, simultaneous method gave excellent results. In all the three methods of dyeing, using two plant parts, the mordants ferrous sulphate and aluminium sulphate show excellent colour strength values. For dyeing of cotton, 1%, 2% and 3% mordant concentrations were used for the present study. Among these three concentrations 3% mordant concentration gave better results.

The colour fastness values of cotton fabrics dyed with the flower of *Spathodea campanulata* and flower of *Cordia sebestena* obtained in this study by using single mordanting method are presented and compared in Table 4.

Plant parts used for dyeing	Mordant used	Method	Properties						Reference
			WF	LF	RF		PF		
					Dry	Wet	Acidic	Alkaline	
Flower of <i>Spathodea campanulata</i>	Ferrous sulphate (3%)	SM	4	5	5	5	5	5	Sandeep bains et al (2003) Shilpa mudgal and Geeta mahale (2002) Bains et al (2003) Vankar et al (2010) Kumar et al (2004) Boonroeng et al (2009)
		PM	4	4	5	5	5	5	
	Aluminium sulphate (3%)	SM	4	5	5	4	5	5	
		PM	4	4	5	5	5	5	
Flower of <i>Cordia sebestena</i>	Ferrous sulphate (3%)	SM	5	5	5	5	5	5	
		PM	5	5	5	5	5	5	
	Aluminium sulphate (3%)	SM	4	5	5	4	4	4	
		PM	5	4	5	5	5	5	
<i>Onosma echioides</i>	Ferrous sulphate (3%)	SM	5	2	5	5	4	5	
	Aluminium sulphate (5%)	SM	5	2	4	3-4	5	5	
<i>Fountain flower</i>	Ferrous sulphate (3%)	SM	4-5	5	4-5	4	4-5	4-5	
<i>Mangifera indica</i>	Ferrous sulphate (2.5%)	SM	5	4	4-5	4	5	5	
	Aluminium sulphate (12.5%)	SM	5	4	4-5	4	5	5	
<i>Colquhounia coccinea</i>	Ferrous sulphate (2.5%)	PM	4-5	4-5	5	5	5	5	
	Aluminium sulphate (12.5%)	PM	4	4	4	4	4	4	
<i>Pongamia pinnato</i>	Ferrous sulphate (2.5%)	SM	-	5	4-5	4-5	-	-	
	Aluminium sulphate (12.5%)	SM	-	5	4-5	4-5	-	-	
Neem tree bark	Aluminium sulphate (12.5%)	PM	3	2-3	4-5	4-5	-	-	

Table 4: Comparison of fastness properties and colour strength of dyed cotton using single mordants

WF-Wash fastness LF-Light fastness PF-Perspiration fastness RF-Rub fastness CS-Colour strength PM-Pre mordanting SM-Simultaneous mordanting

From the results, it was observed that among the two plant parts, *Cordia sebestena* showed better light fastness properties. Similar rub fastness and perspiration fastness values were obtained. *Cordia sebestena* showed better wash fastness when compared with *Spathodea campanulata* dyed cotton fabrics.

In all the three dyeing methods, simultaneous method gave excellent results. In all the three methods of dyeing, using two plant parts, the mordants ferrous sulphate and aluminium sulphate show excellent results. Among the three concentrations 3% mordant concentration gave better fastness results.

Similar results were obtained in the previous study reported by Das et al (2008). The present study shows excellent wash fastness (GS : 4) and light fastness (GS :4) when compared with Das et al (2007) study (WF : 2-3 and LF : 3). A better light fastness (GS : 8) was reported by Sharada devi et al (2002) in pre mordanting method.

CONCLUSION

From the comparative study of fastness properties and colour strength of the dyed cotton samples, *Spathodea campanulata* in simultaneous mordanting method with 3% mordant combination gives better results as compared to the *Cordia sebestena* dye.

ACKNOWLEDGEMENT

The authors are thankful to Mr P Santharaj, Department of Textile Processing, Erode Institute of Technology for his support in the analysis of fastness properties of the dyed samples of this work.

REFERENCES

1. Adeel S, Ali S, Bhatti IA and Zsila F. Dyeing of cotton fabric using Pomegranate (*Punica Granatum*) aqueous extract. *Asian Journal of Chemistry* 2009; 21(5): 3493-3499.
2. Anderson B. *Creative Spinning, Weaving and Plant dyeing*. Angus and Robinson, Singapore 1971:24 -28.
3. Anitha K., Prasad SN. Developing multiple natural dyes from flower parts of Gulmohur. *Current Science* 2007; 92(12):1681-1682.
4. Mahangade RR, Varadarajan PV, Verma JK and Bosco H. New Dyeing Techniques for Enhancing Color Strength and Fastness Properties of Cotton Fabric Dyed with Natural Dyes. *Indian Journal of Fibre and Textile Research* 2009; 34:279-282.
5. Goodarzian H and Ekrami E. Wool Dyeing with Extracted Dye from Pomegranate (*Punica Granatum*) Peel. *World Applied Science Journal* 2010;8(11):1387-1389.
6. Gulrajani ML and Gupta Deepti. *Natural Dye and their Application to Textiles*. Department of Textile Technology, IIT, Delhi 1992:25.
7. Kumaresan M, Palanisamy PN and Kumar PE. Dyeing of cotton and silk using flower of *Spathodea campanulata*: Effects of mordanting and colour fastness properties. *Journal of Basic and Applied Scientific Research* 2011; 1(8): 933-941.
8. Kumaresan M, Palanisamy PN and Kumar PE. Dyeing of cotton using flower of *Cordia sebestena*: Effects of mordanting and fastness properties. *Journal of Asian Scientific Research* 2011; 1(4):137-142.
9. Sandeep Bains, Singh OP, Ganganpreet Goraya and Manpreet Kang. Dyeing of Cotton with Golden drop dye. *Journal of the Textile Association* 2003:183-186.
10. Vankar PS, Shankar R and Mahanta D. Natural dyeing of wool and cotton with extract of *Colquhounia coccinea*. *Asian Dyer* 2010:51-54.
11. Das D, Maulik SR and Bhattacharya SC. Colouration of wool and silk with *Rheum emodi*. *Indian Journal of Fibre and Textile Research* 2008; 33:163-170.
12. Das D, Maulik SR and Bhattacharya SC. Dyeing of wool and silk with *Bixa orellana*. *Indian Journal of Fibre and Textile Research* 2007; 32: 366-372.

13. Sharada Devi A, Sumanthy BS and Katyayini VKLT. Eclipta prostate -A weed rich in coloured pigments for silk. Man Made Textiles in India 2002:181-189.



M.KUMARESAN^{1*}, P.N.PALANISAMY² and P.E.KUMAR³

¹Associate Professor, Department of Chemistry, M P Nachimuthu M Jaganathan Engineering College, Chennimalai, Erode, Tamilnadu, India

²Professor and Head, Department of Chemistry, Kongu Engineering College Perundurai, Erode, Tamilnadu, India

³Associate Professor, Department of Chemistry, Erode Arts and Science College, Erode, Tamilnadu, India.

E-mail: mkumsrenu@yahoo.com , drmkumaresan2012@gmail.com